

## 466 – Metal Detectable Glasses Cord

**Document Number: 773**

**Date Of Issue: 26/7/2019**

**Revision Number: 2**

**Date of Revision: 26/7/2023**




| Product Code                       | Product Description  | Product Colour |
|------------------------------------|--|----------------|
| <b>466-P75-X06</b>                 | Detectable Glasses String Silicone Rubber Blue Pack of 25      | Blue           |
| <b>Material</b>                    | Polypropylene 56 decitex <i>(ISO 9001 accredited supplier)</i> |                |
| <b>Width (qty of yarn strands)</b> | 10   |                |
| <b>Size</b>                        | 74 cm  |                |
| <b>Weight</b>                      | 0.5 grams  |                |
| <b>Metal Detectable</b>            | Nickle free non rust   |                |

| Property  | Units   | Typical Value | Test Method          |
|---|---------|---------------|----------------------|
| <b>Hardnes</b>                                  | Shore A | 67            | ASTM D2240           |
| <b>Tensile Strength</b>                         | MPa     | 9.0           | BS ISO 37            |
| <b>Elongation to Break</b>                      | %       | 340           | BS ISO 37            |
| <b>Tear Strength</b>                            | N/mm    | 15.7          | BS ISO 34-1 method C |
| <b>Compression Set<br/>25% for 24hrs @ 150c</b> | %       | 14,1          | BS 903 pt A6 type B  |
| <b>Magnetic Pull</b>                            | MM      | 6.5           | SEWI/700 ISS 2       |
| <b>Temperature</b>                              | C       | -60 TO 200    |                      |

*Colour dark blue 60 shore*

*The above contains only ingredients that are listed by the American food and drugs administration (FDA) inder 21 CFR number 177-2600 & EC1935/2004*

No warranty is given or implied with respect to this information or patent infringement. Detectamet Ltd do not accept liability for loss or damage arising from the use of this information. Results are based on a test sample, our general experience and information from our suppliers. Data and results must be confirmed by the buyer by testing for its intended conditions of use.



**Helen Morrison**  
Group Managing Director

